

102.2 - Cobalt Base Alloys (chip and disk forms)

Technical Contact: john.sieber@nist.gov

PLEASE NOTE: The tables are presented to facilitate comparisons among a family of materials to help customers select the best SRM for their needs. For specific values and uncertainties, the certificate is the only official source.

SRM	Description	Unit of Issue	C	Mn	P	S	Si	Cu	Ni	Cr	V	Fe	W	Co	N	Al
862	High Temp. Alloy L605	100 g	0.120	1.59	0.002	0.0008	0.017	0.0010	9.74	20.0	0.005	1.80	15.1	51.5	0.026	(
1242	High Temp. Alloy L-605	disk	0.126	1.58	0.002	0.0007	0.016	0.0010	9.78	20.0	0.005	1.80	15.1	51.5	0.026	(
1775	MP 35N Refractory Alloy	disk	0.0051	0.0121	0.0006	0.013	0.02	0.0046	34.91	20.4	0.0095	0.91	0.02	33.3	0.002	0.024
2175	MP 35N Refractory Alloy	150 g	0.0051	0.0121	0.0006	0.0013	0.02	0.0046	34.91	20.4	0.0095	0.91	0.02	33.3	0.002	0.024

Values in parentheses are not certified and are given for information only.

102.2 - Cobalt Base Alloys (chip and disk forms)

Technical Contact: john.sieber@nist.gov

PLEASE NOTE: The tables are presented to facilitate comparisons among a family of materials to help customers select the best SRM for their needs. For specific values and uncertainties, the certificate is the only official source.

Ta

(

(

Values in parentheses are not certified and are given for information only.